

22. A structure according to claim 21, further comprising a layer of binder between the second and the third layer.

23. A structure according to claim 21, in which the binder comprises:

- 5 to 30 parts by weight per hundred of a polymer (D) which itself comprises a mixture of a polyethylene (D1) with a density of from 0.910 to 0.940 g/cm<sup>3</sup> and of a polymer (D2) selected from the group consisting of elastomers, very low density polyethylenes and metallocene polyethylenes, the mixture (D1) + (D2) being co-grafted with an unsaturated carboxylic acid,
- 95 to 70 parts by weight per hundred of a polyethylene (E) with a density of from 0.910 to 0.930 g/cm<sup>3</sup>,
- the mixture of (D) and (E) being such that:
  - its density is from 0.910 to 0.930 g/cm<sup>3</sup>,
  - the content of grafted unsaturated carboxylic acid is between 30 and 10,000 ppm, and
  - the melt flow index, measured by ASTM D 1238, at 190°C and 2.16 kg, is between 0.1 and 3 g/10 min.

24. A structure according to claim 23, in which the density of the binder is from 0.915 to 0.920 g/cm<sup>3</sup>.

25. A structure according to claim 23, in which (D1) and (E) are LLDPEs which have the same comonomer.

26. A structure according to claim 21, in which the binder comprises:

- 5 to 30 parts by weight per hundred of a polymer (F) which itself comprises a mixture of a polyethylene (F1) with a density of from 0.935 to 0.980 g/cm<sup>3</sup> and of a polymer (F2) selected from the group consisting of elastomers, very low density polyethylenes and ethylene copolymers, the mixture (F1) + (F2) being co-grafted with an unsaturated carboxylic acid,
- the mixture of (F) and (G) being such that:
  - its density is from 0.930 to 0.950 g/cm<sup>3</sup>,
  - the content of grafted unsaturated carboxylic acid is between 30 and 10,000 ppm,
  - the metal flow index, measured by ASTM D 1238 at 190°C and 21.6 kg, is between 5 and 100 g/10 min.

27. A structure according to claim 21, in which the binder is a polyethylene grafted with maleic anhydride, having a melt flow index, measured by ASTM D 1238 at 190°C and 21.6 kg, of 0.1 to 3 g/10 min, a density of from 0.920 to 0.930 g/cm<sup>3</sup> and containing 2 to 40% by weight of insolubles in n-decane at 90°C.

28. A structure according to claim 27, in which the grafted polyethylene is diluted in a non-grafted polyethylene such that the binder is a mixture of 2 to 30 parts by weight per hundred of a grafted polyethylene with a density of from 0.930 to 0.980 g/cm<sup>3</sup> and from 70 to 98 parts by weight per hundred of a non-grafted polyethylene with a density of from 0.910 to 0.940 g/cm<sup>3</sup>.

29. A structure according to claim 21, in which the binder is a mixture consisting of a HDPE, LLDPE, VLDPE or LDPE polyethylene, 5 to 35% by weight of a grafted metallocene polyethylene and 0 to 35% by weight of an elastomer, based on a total of 100% by weight.

30. A structure according to claim 21, in which the polyamide of the third layer is a copolyamide.

31. A structure according to claim 21, wherein the third layer comprises a polyolefin (B) which comprises:

- (i) a high density polyethylene and
- (ii) a mixture of a polyethylene (C1) and a polymer (C2) selected from the group consisting of elastomers, very low density polyethylenes and ethylene copolymers, the mixture (C1) + (C2) being co-grafted with an unsaturated carboxylic acid.

32. A structure according to claim 21, wherein the third layer comprises a polyolefin (B) which comprises:

- (i) a high density polyethylene,
- (ii) a polymer (C2) selected from the group consisting of elastomers, very low density polyethylenes and ethylene copolymers, the polymer (C2) being grafted with an unsaturated carboxylic acid and
- (iii) a polymer (C'2) selected from the group consisting of elastomers, very low density polyethylenes and ethylene copolymers.

33. A structure according to claim 21, wherein the third layer comprises a polyolefin (B) which comprises:

- (i) a polypropylene and
- (ii) a polyolefin prepared by reacting a polyamide (C4) with a copolymer (C3) comprising propylene and a grafted or copolymerized unsaturated monomer X.

34. A structure according to claim 21, wherein the third layer comprises a polyolefin (B) which comprises:

- (i) a LLDPE, VLDPE or metallocene polyethylene and
- (ii) an ethylene-alkyl (meth)acrylate-maleic anhydride copolymer.

35. A structure according to claim 21, in which the polyamide (A) of the third layer is selected from the group consisting of:

mixtures of (i) a polyamide and (ii) a copolymer containing polyamide-6 blocks and polytetramethylene glycol blocks, and

mixtures of (i) a polyamide and (ii) a copolymer containing polyamide-12 blocks and polytetramethylene glycol blocks,

the weight ratio of the amounts of copolymers (ii) and polyamides (i) being from 10:90 to 60:40.

36. A structure according to claim 35, in which the third layer comprises a polyolefin B, which comprises (i) a LLDPE, VLDPE or metallocene polyethylene and (ii) an ethylene-alkyl (meth)acrylate-maleic anhydride copolymer.

37. A structure according to claim 35, in which the third layer comprises a polyolefin (B) which comprises two functionalized polymers comprising at least 50 mol% of ethylene units and which is capable of reacting to form a crosslinked phase.

38. A structure according to claim 22, in which the binder comprises:

- 5 to 30 parts by weight per hundred of a polymer (D) which itself comprises a mixture of a polyethylene (D1) with a density of from 0.910 to 0.940 g/cm<sup>3</sup> and of a polymer (D2) selected from the group consisting of elastomers, very low density polyethylenes and metallocene polyethylenes, the mixture (D1) + (D2) being co-grafted with an unsaturated carboxylic acid,
- 95 to 70 parts by weight per hundred of a polyethylene (E) with a density of from 0.910 to 0.930 g/cm<sup>3</sup>,
- the mixture of (D) and (E) being such that:
  - its density is from 0.910 to 0.930 g/cm<sup>3</sup>,
  - the content of grafted unsaturated carboxylic acid is between 30 and 10,000 ppm, and
  - the melt flow index, measured by ASTM D 1238 at 190°C and 2.16 kg, is between 0.1 and 3 g/10 min.

39. A structure according to claim 22, in which the binder comprises:

- 5 to 30 parts by weight per hundred of a polymer (F) which itself comprises a mixture of a polyethylene (F1) with a density of from 0.935 to 0.980 g/cm<sup>3</sup> and of a polymer (F2) selected from the group consisting of elastomers, very

low density polyethylenes and ethylene copolymers, the mixture (F1) + (F2) being co-grafted with an unsaturated carboxylic acid,

- 95 to 70 parts by weight per hundred of a polyethylene (G) with a density of from 0.930 to 0.950 g/cm<sup>3</sup>, the mixture of (F) and (G) being such that:
- its density is from 0.930 to 0.950 g/cm<sup>3</sup>,
  - the content of grafted unsaturated carboxylic acid is between 30 and 10,000 ppm,
  - the melt flow index, measured by ASTM D 1238 at 190°C and 21.6 kg, is between 5 and 100 g/10 min.

40. A device for transferring and/or storing fluids comprising a structure according to claim 21 such that the fluids so stored and/or transferred are in contact with the third layer side of the structure.

41. A device according to claim 40, wherein the device is a tube, a tank, a chute, or a bottle.

42. A device according to claim 40, wherein the device is a container.